

01.11.2025/Revision Number: 00

SOLIDEX WATER RESISTANT GYPSUM PLASTERBOARD**DEFINITION**

-Solidex is a water resistant gypsum plasterboard that has structural strength and durability above standards, is more durable with its strong chamfered edges, has the feature of adapting to movement.

APPLICATION AREA

- It is used in interior partition wall, curtain wall and suspended ceiling applications where water resistance is required.

WARNINGS AND RECOMMENDATIONS

- When carrying plasterboards by hand, it is recommended that 2 people carry them so that the long edge is parallel to the ground.
- If it will be transported by forklift, care must be taken that the forklift used has sufficient carrying capacity and that the forklift operator is qualified and experienced.
- Plasterboards should never lean vertically.
- The plates to be applied must be dry and have a smooth surface. Plasterboards that become damp and deformed due to adverse stock conditions should not be used in the stock area.
- It is not appropriate to apply plasterboards whose surface temperature exceeds 50 °C during storage.
- Solidex water resistant gypsum plasterboard should not be used as a waterproofing material.
- It is not recommended to apply rough plaster on Solidex water-resistant plate.

APPLICATION

- The metal framework of the partition wall, curtain wall or suspended ceiling to be created in accordance with the plan is marked on the floor or ceiling.
- After measurement and marking, the metal skeleton is created in accordance with the application conditions.
- Plaster plates; In cases where it needs to be cut, it is cut from the front surface with a utility knife using a jig. The tip of the utility knife should cut through the paper and enter the core. Plasterboards are bent against the cut surface, the paper connection on the back side is cut with a utility knife and the pieces are separated from each other.
- After the plasterboards are cut, the cut edges can be smoothed using a grater.
- Artificial chamfers should be made on the cut edges and the non-chamfered edges of the plates with suitable tools at an angle of approximately 45°.
- Artificial chamfer opening will allow more smooth and comfortable joint filling plaster application.
- Plasterboards should be fixed at their joints in such a way that there is no gap between them and the screws should be perpendicular to the edges of the plasterboard at a distance of at least 10 - 15 mm.
- In adhesive curtain wall applications, plaster plates are adhered to the existing building wall using Gypsum Plate Adhesive Plaster.
- After fixing, Grouting gypsum plaster is applied in 3 layers to the joints where screw heads and joint tape have been applied.
- Satin Finish Plaster is applied in a maximum thickness of 1 mm (1 kg/m²) to make the surface ready for the final coat.

REFERENCE STANDARD

-TS EN 520+A1

STORAGE

- It should be stored in a dry and moisture-free environment, on a flat surface, not in direct contact with the ground, and not exposed to direct sunlight and any external weather or wetting conditions.
- The contact of the plates with the ground should be broken by placing wedges under the plates, parallel to their short edges, starting from a maximum of 10 cm from the edges and at a maximum interval of 50 cm.
- A maximum of 6 pallets should be stored on top of each other (height max. 450 cm) and the wedges between the pallets should be aligned.

01.11.2025/Revision Number: 00

TECHNICAL SPECIFICATIONS

Nominal Thickness	9.5mm	12.5mm	15mm	18mm
Average Weight (kg/m ²)	≤ 8.00	≤ 9.50	≤ 12.00	≤ 14.50
Bending Breaking Load Short Side (N)	≥ 160	≥ 210	≥ 250	≥ 303
Bending Breaking Load Long Side (N)	≥ 400	≥ 550	≥ 650	≥ 774
Edge Type	Blunt Edge, Thinned Edge			
Thermal Conductivity (W/mK)	0,25			
Total Water Absorption (%)	H1	≤ 5		
	H2	≤ 10		
	H3	≤ 25		
Surface Water Absorption (g/ m ²)	H1	< 180		
	H2	< 220		
	H3	< 300		
Coefficient of Resistance to Water Vapor Transmission (μ)	10			
Fire Reaction Class	A2-s1-d0			

	Kod	Width mm	Length mm	Packing
9,5 mm	8911-H1	1200	2000	34-118
		1200	2200	34-118
		1200	2400	34-118
		1200	2500	34-118
		1200	3000	34-118
	8911-H2	1200	2000	34-118
		1200	2200	34-118
		1200	2400	34-118
		1200	2500	34-118
		1200	3000	34-118
	8911-H3	1200	2000	34-118
		1200	2200	34-118
		1200	2400	34-118
		1200	2500	34-118
		1200	3000	34-118
12,5 mm	8912-H1	1200	2000	26-90
		1200	2200	26-90
		1200	2400	26-90
		1200	2500	26-90
		1200	3000	26-90
	8912-H2	1200	2000	26-90
		1200	2200	26-90

01.11.2025/Revision Number: 00

		1200	2400	26-90
		1200	2500	26-90
		1200	3000	26-90
	8912-H3	1200	2000	26-90
		1200	2200	26-90
		1200	2400	26-90
		1200	2500	26-90
		1200	3000	26-90
15 mm	8913-H1	1200	2000	22-74
		1200	2200	22-74
		1200	2400	22-74
		1200	2500	22-74
		1200	3000	22-74
	8913-H2	1200	2000	22-74
		1200	2200	22-74
		1200	2400	22-74
		1200	2500	22-74
		1200	3000	22-74
	8913-H3	1200	2000	22-74
		1200	2200	22-74
		1200	2400	22-74
		1200	2500	22-74
		1200	3000	22-74
18 mm	8914-H1	1200	2000	18-62
		1200	2200	18-62
		1200	2400	18-62
		1200	2500	18-62
		1200	3000	18-62
	8914-H2	1200	2000	18-62
		1200	2200	18-62
		1200	2400	18-62
		1200	2500	18-62
		1200	3000	18-62
	8914-H3	1200	2000	18-62
		1200	2200	18-62
		1200	2400	18-62
		1200	2500	18-62
		1200	3000	18-62